

# Sollanalysen

## Kaltzähe Stähle

WSt-Nr.	Werkstoff- bezeichnung	Norm	C (%)	Si (%)	Mn (%)	P (%)	S (%)	Cr (%)
1.6217	13 MnNi 6-3	Stahlschlüssel 2007	≤ 0,16	≤ 0,50	0,85-1,70	≤ 0,025	≤ 0,015	-
1.7219	G 26 CrMo 4	Stahlschlüssel 2007	0,22-0,29	≤ 0,35	0,50-0,80	≤ 0,030	≤ 0,025	0,90-1,20

WSt-Nr.	Werkstoff- bezeichnung	Norm	Ni (%)	Mo (%)	Nb (%)	V (%)	W (%)	Cu (%)
1.6217	13 MnNi 6-3	Stahlschlüssel 2007	0,30-0,85	-	-	≤ 0,05	-	-
1.7219	G 26 CrMo 4	Stahlschlüssel 2007	-	0,15-0,30	-	-	-	-

WSt-Nr.	Werkstoff- bezeichnung	Norm	Al (%)	Co (%)	N (%)
1.6217	13 MnNi 6-3	Stahlschlüssel 2007	-	-	-
1.7219	G 26 CrMo 4	Stahlschlüssel 2007	-	-	-